Serial No. 09/805,483 Filed March 13, 2001 Response to Office Action

## Amendments to the Claims

Please cancel claims 12, and 39-50. Claims 1, 5, 6, 8-11, and 13 are pending in the application.

## Listing of the Claims

- (presently amended) A microparticle formed from macromers having a
  polymeric backbone comprising units having a 1,2-diol or 1,3-diol structure and at least two
  pendant chains bearing crosslinkable groups, wherein the crosslinkable groups are crosslinked
  via free radical polymerization.
  - 2. 4. (cancelled)
- 5. (previously presented) The microparticle of claim 1, wherein the backbone polymer comprises poly(vinyl alcohol) (PVA) and copolymers thereof.
- 6. (previously presented) The microparticle of claim 1, wherein the macromer has the formula:

in which R is a linear or branched  $C_1$ - $C_8$  alkylene or a linear or branched  $C_1$ - $C_{12}$  alkane;  $R_1$  is hydrogen, a  $C_1$ - $C_6$  alkyl, or a cycloalkyl;  $R_2$  is hydrogen or a  $C_1$ - $C_6$  alkyl; and  $R_3$  is an olefinically unsaturated electron attracting copolymerizable radical having up to 25 carbon atoms.

- 7. (cancelled)
- 8. (previously presented) The microparticle of claim 1, further comprising an active agent.
- 9. (previously presented) The microparticle of claim 8, wherein the microparticle releases the active agent over a period of time ranging from about 1 day to 6 months.

BIOCURE 190 2
PAGE 3/7 \* RCVD AT 9/14/2005 8:44:59 AM [Eastern Daylight Time] \* SVR:USPTO-EFXRF-6/24 \* DNIS:2738300 \* CSID:4043774015 \* DURATION (mm-ss):03-40

Serial No. 09/805,483 Filed March 13, 2001 Response to Office Action

- 10. (previously presented) The microparticle of claim 1, wherein the microparticle is biodegradable.
- 11. (previously presented) The microparticle of claim 1, further comprising a contrast agent.
- 12. (cancelled) The microparticle of claim 1, wherein the crosslinkable groups are crosslinked via free radical polymerization.
- 13. (presently amended) The microparticle of claim [11] 1, wherein the free radical polymerization is redox initiated.
  - 14. 50. (cancelled)